

Typical performance values for the Trimcell Range are as follows:

	Nominal Roll Length	Total Weight	Coating Weight	Average Thickness	Bursting Strength	Coating Adhesion min.	Elongation (100N)	Relaxation (10 Min.)	
	m	g/m ²	g/m ²	mm	kN/m ²	N/50mm	%	%	
Legend	30	625	555	1.00	785	26	12	L 0.8	L
						68		T 8.0	T
						10		L 0.8	L
Classic	30	500	430	0.90	760	26	97	T 8.8	T

Both qualities are 1.37m wide

Flame Retardant, Non Feu, Schwerentflammbarkeit, Ignifugazione, Combustión Retardada

EN 1021 - 1 Furniture and Furnishings Regulations 1988, Schedule 4 and 5

EN 1021 - 2 Méthode du Brûleur Electrique: Classification M4

CAA - 8 BS 7176 Low Hazard

FMVSS 302

Cleaning, Nettoyage, Reinigung, Pulizia, Limpieza

Clean with a damp soapy cloth and rinse well with clean water. A soft brush can be used for heavy soiling. Do not use solvents, bleaches, abrasives, synthetic detergents, wax polishes or aerosol sprays.

Nettoyer régulièrement avec une éponge ou une brosse, et de l'eau savonneuse, suivi d'un rinçage léger. Ne pas utiliser: agents blanchissants, dissolvants, produits abrasifs, détergents, cire et cirage, aérosols.

Einfache Reinigung mit einem feuchten seifigen Tuch, danach mit klarem Wasser abwischen. Bei größerer Verschmutzung empfiehlt sich eine weiche Bürste. Bitte keine Chemikalien und keine Wachspolituren, Scheuer- und Scheifmittel verwenden.

Pulite con un tessuto inumidito e insaponato e risciacquate bene con acqua pulita. Per macchie più difficili potete usare una spazzola morbida. Non usate solventi, candeggi, abrasivi, detergenti sintetici, liquidi per lucidare o sprays aerosol.

Limpiar con una gamuza ligeramente húmeda y con un poco de jabón. Puede utilizarse un cepillo suave para manchas fuertes. No utilizar disolventes, agentes blanqueadores, abrasivos, detergentes sintéticos, ceras o sprays que contengan aerosoles.

TRIMCELL IS NOT SUITABLE FOR CONTRACT UPHOLSTERY. FOR SUCH APPLICATIONS, WE RECOMMEND THAT EITHER THE CHIEFTAIN OR LIONELLA COLLECTION OF CONTRACT UPHOLSTERY VINYL IS USED.



FM22699
BSEN ISO 9002

Trimproof UK Information Office
Tel: 01827 289455 Fax: 01827 289599

Trimproof Customer Service
Fax: + 353 46 37669
Email: customerservices@trimproof.ie

Trimproof Limited
Trim, Co. Meath, Ireland.
Tel: + 353 46 31396
Fax: + 353 46 31756

Email: b.d.group@trimproof.ie
Website: www.iol.ie/trimproof

Trimproof Euro - Depot
Tel: + 33 (0) 320 258467
Fax: + 33 (0) 320 258468